Rubber/Ingredient name	Typical Specific Gravity
Natural Rubber	0.93
Isoprene Rubber	0.92
SBR1502	0.93
SBR1712	0.95
SBR1723	0.94
SBR1783	0.95
SBR1739	0.96
Polybutadiene Rubber	0.92
Butyl Rubber	0.92
Chloro Butyl Rubber	0.92
Bromo Butyl Rubber	0.93
EPM/EPDM	0.87
NBR	0.96
Chloroprene Rubber	1.24
CSM	1.13
TM	1.31
FKM	1.60
Reclaim Rubber (WTR)	1.12
Carbon black	1.80
Ppt.hydrated silica	2.00
calcium silicate	2.10
aluminium silicate	2.10
Ppt.calcium carbonate	2.70
china clay	2.62
calcined clay	2.68
whiting	2.70
barytes(ground)	4.45
Magnesium carbonate	2.22
Soap stone	2.72
Ppt.Zinc carbonate	3.30
magnesium oxide	3.20
Mica powder	2.95
aluminium hydroxide	2.42
paraffinic oil	0.88
napthenic oil	0.90
aromatic oil	0.96
castor oil	0.96
pine tar	1.08
dibutylphthalate	1.04
dioctylphthalate	0.98
dibutylsebacate	0.94
tricresylphosphate	1.13
dioctyladipate	0.92
C.I Resin	1.11
Factice	1.06
Mineral rubber	1.04
wood rosin	1.08
paraffinic wax	0.90
microcrystalline wax	0.93
diethylene glycol	1.12
stearic acid	0.85
zinc oxide	5.60
zinc stearate	1.05
zinc sulphide	3.92
red lead	8.62
Calcium oxide	2.20
Soluble sulphur	2.07

Rubber/Ingredient name	Typical Specific Gravity
Insoluble Sulphur (20% OT)	1.60
MBT	1.52
MBTS	1.54
ZMBT	1.70
Accelerator F	1.39
CBS	1.28
TBBS	1.28
MBS	1.36
DCBS	1.23
TMTM	1.40
TMTD	1.42
ZDMC	1.70
ZDEC	1.48
ZDBC	1.27
ZBEC	1.42
DTDM	1.30
PVI(CTP)	1.30
DPG	1.19
DOTG	1.18
HMT	1.02
SP	1.08
TDQ	1.10
IPPD	1.10
6 PPD	0.99
DTPD	1.26
Peptiser PCTP	2.33
Peptiser DBD	2.00
DNPT Blowing agent	1.43
Titaniumdioxide	3.90
ultramarine blue	2.35
red oxide	5.10
PF resin	1.20