

TECHNICAL DATA SHEET

(Neodymium catalyst based Polybutadiene Rubber)

Material:

Cisamer 700 is a solution polymerized High Cis – 1,4 Polybutadiene rubber produced using complex stereospecific organometallic catalyst based on JSR technology, It provides good processability with low rolling resistance versus other conventional PBR grades.

ELASTOMER PROPERTIES

| S.No. | Test | Unit | Typical Value | Test Method |
|-------|----------------------|---------------|---------------|-------------|
| 1.1 | Raw Mooney Viscosity | ML(1+4)@100°C | 39 | ASTM D 1646 |
| 1.2 | Volatile Matter | Wt% | 0.4 | ASTM D 5668 |
| 1.3 | Ash | Wt% | 0.1 | ASTM D 5667 |
| 1.4 | Cis-content | % | 96 | FTIR |

ASTM D 3189* COMPOUND PROPERTIES (FOR REFERENCE)

| S.No. | Test | Unit | Typical Value | Test Method | | |
|-------|--|---------------|---------------|-------------|--|--|
| 2 | Compound Mooney Viscosity | ML(1+4)@100°C | 54 | ASTM D 1646 | | |
| 3 | Rheological Properties (MDR - 160 $^{\circ}$ C; ± 1 degree arc; 100 cpm) | | | | | |
| 3.1 | Minimum Torque ML | dN.m | 2.5 | ASTM D 5289 | | |
| 3.2 | Maximun Torque MH | dN.m | 17.8 | ASTM D 5289 | | |
| 3.3 | Ts1 | minutes | 2.5 | ASTM D 5289 | | |
| 3.4 | Tc50 | minutes | 5.8 | ASTM D 5289 | | |
| 3.5 | Tc90 | minutes | 10.1 | ASTM D 5289 | | |
| 4 | Physical Properties (35 min. @ 145°C) | | | | | |
| 4.1 | Tensile Strength | MPa | 15.8 | ASTM D 412 | | |
| 4.2 | Modulus@300% | MPa | 9.8 | ASTM D 412 | | |
| 4.3 | Elongation at Break | % | 420 | ASTM D 412 | | |

*ASTM D 3189:

BR - 100; IRB#8 - 60; ZnO - 3; St. Acid - 2.0; Napthenic Oil - 15; S - 1.5; TBBS - 0.9

PACKAGING :

Cisamer 51 is supplied in 35 kg bales wrapped with polyethylene film for further packaging.

Shelf Life / Storage Condition:

Material should be covered and stored in a cool, dry and well ventilated place at a temperature below 40°C. Proper care needs to be taken so that the material does not get exposed to direct sunlight, ultraviolet light or rain water. For prolonged storage, it is recommended to cover the material with black polythene film to protect it from direct sunlight. Under proper storage conditions as described above, product shelf life of Relflex[™] Cisamer PBR 51 grade is 12 months from the date of manufacturing.



Reliance Corporate Park, Relflex Elastomers Business Group, 8A FF, Ghansoli, Navi Mumbai - 400 701. Tel: +91 22 44780431 | Fax: +91 22 44710135 rubberbusiness@ril.com | www.ril.com **MARCH 2015**